



Product Information

Updated : Mar.2014

General Description

S-60 is suspension PVC with excellent gelation 、flow and high transparency properties.

Main Applications

Used for extrusion, injection blow molding articles and calendering process of rigid film, sheet. It also used for pipe fitting.

Resin Properties

Parameter	Typical Value	Unit	Test Method
K-Value	60~62	-	DIN53726
Degree of Polymerization	800 ± 50	-	GB/T 5761-2018
Particle Size	Max. 0.01	%	GB/T 21843-2008
Apparent Bulk Density	0.55 ± 0.02	g/cm ³	GB/T 20022-2005
Cold Plasticizer Absorption	18 ± 2.0	%	GB/T 3400-2002
Volatiles	Max. 0.3	%	GB/T 2914-2008
VCM Residual	Max. 1	ppm	GB/T29874 -2013
Foreign Matter	Max. 20	PC/100g	GB/T 9348-2008
魚眼 Fish Eye	Max. 20	PC/400cm ²	GB/T 4611-2008

*K Value (reference) from a viscosity conversion table.

Packaging

Paper bag(25kg)、Jumbo bag

Certificate Numbers

ISO 9001:2008 Certificate TW06/03198
 ISO 14001:2004 Certificate TW06/01039EM
 OHSAS 18001:2007 Certificate TW06/0148