



Product Information

Updated : Mar.2020

General Description

S-65 is suspension PVC with good plasticizer absorption and good heat stability.

Main Applications

This resin is intended for soft application, flexible film, and other flexible articles. It also suit for cables and wires application.

Resin Properties

Parameter	Typical Value	Unit	Test Method
K-Value	66.0~68.0	-	GB/T 5761-2018
Degree of Polymerization	1050 ±50	-	
Particle Size	Max. 0.01	%	GB/T 21843-2008
Apparent Bulk Density	0.53± 0.03	g/cm ³	GB/T 20022-2005
Cold Plasticizer Absorption	Min. 24.0	%	GB/T 3400-2002
Volatiles	Max. 0.3	%	GB/T 2914-2008
VCM Residual	Max. 1.0	ppm	GB/T 29814-2013
Foreign Matter	Max. 16	PC/900 cm ²	GB/T 9348-2008
Fish Eye	Max. 20	PC/400cm ²	GB/T 4611-2008

*K Value (reference) from a viscosity conversion table.

Packaging

PP woven bag (25kg)、Jumbo bag

Certificate Numbers

ISO 9001:2015

Certificate 00115Q254RIM/3302